



Light stabilizer for styrene polymers

Supplied in shape of:

Mixture, Granule.

Active agent:

Light stabiliser masterbatch.

Area of use:

HECO®STAB 338 PS is suitable for use in polystyrene and ABS.

Recommended dose:

HECO®STAB 338 PS is added in the range of 2.0 - 6.0 %.

Properties:

HECO®STAB 338 PS prevents radical polymer degradation initiated by UV light and thus protects the plastic to be processed from UV light exposure.

1.000.0 kg (40 sacks at 25.0 kg) / pallet, net.

Safety Precautions

Foodstuff regulation:

The mentioned product is a raw material for the plastics processing industry. Conformity for food contact applications in the plastics sector is not available.

Storage:

No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

Handling:

The precautions and hygienic measures usual in the handling of any chemical product should be observed.

In case of fire:

In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water is unsuitable.

HECOPLAST[®] and **HECO**[®] are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features. Specific field tests are being recommended under any circumstance.