

# 372 PP

## Light stabilizer

### Supplied in shape of:

Mixture, Granule.

### Active agent:

Light stabiliser masterbatch.

### Area of use:

**HECO®STAB 372 PP** is suitable for use in polypropylene articles under extreme climatic conditions.

### Recommended dose:

**HECO®STAB 372 PP** is added in a range of 1.0 - 10.0 %.

### Properties:

**HECO®STAB 372 PP** is based on a combination of sterically hindered amines that prevent radical polymer degradation initiated by UV light and thus protect the plastic to be processed from UV light exposure.

### Pallet size:

1000.0 kg (50 sacks at 20.0 kg) / pallet, net.

### Safety Precautions

#### Foodstuff regulation:

The mentioned product is a raw material for the plastics processing industry. Conformity for food contact applications in the plastics sector is not available.

#### Storage:

No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

#### Handling:

The precautions and hygienic measures usual in the handling of any chemical product should be observed.

#### In case of fire:

In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water is unsuitable.

**HECOPLAST®** and **HECO®** are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features.  
Specific field tests are being recommended under any circumstance.

**HECOPLAST®** GmbH Kunststoffadditive, Bremke 17, D - 58638 Iserlohn Telephone + 49 2371 / 797 61-0 — E-Mail: [info@hecoplast.de](mailto:info@hecoplast.de)