

900 C

Blowing and Nucleating Agent

Supplied in shape of:

Powder.

Active agent:

Blowing and nucleating agent.

Area of use:

HECO®FOAM 900 C is suitable for processing various thermoplastic polymers in injection moulding and extrusion.

Recommended dose:

HECO®FOAM 900 C is dosed in the following ranges:

- 0.2 - 0.5 % extrusion (weight reduction)
- 0.1 - 0.3 % injection moulding (against sink marks)
- 0.5 - 1.5 % injection moulding (weight reduction)
- 0.1 - 0.5 % direct gassing (nucleation and cell regulation)

Properties:

HECO®FOAM 900 C is a chemical, endothermic blowing and nucleating agent. As a nucleating agent, it achieves an extremely fine and consistent cell structure. It is suitable for injection moulding, extrusion and direct gassing. The activation temperature is 150 °C. To avoid premature gassing in the feed zone, the temperature here should be as low as possible within the processing range of the polymer (e.g. 150 - 170 °C). For an ideal gas yield, a temperature of 220 °C is recommended.

Pallet size:

On demand.

Safety Precautions

Foodstuff regulation:

Approval according to EU (Regulation) No. 10/2011.

Approval according to the US FDA, see "Food Contact Approvals".

Storage:

No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

Handling:

The precautions and hygienic measures usual in the handling of any chemical product should be observed.

In case of fire:

In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water is unsuitable.

HECOPLAST® and **HECO®** are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features.

Specific field tests are being recommended under any circumstance.

HECOPLAST® GmbH Kunststoffadditive, Bremke 17, D - 58638 Iserlohn Telephone + 49 2371 / 797 61-0 – E-Mail: info@hecoplast.de