

# 020 PP

## Slip Additive for improving the Surface Scratch Resistance

### Supplied in shape of:

Mixture, Granule.

### Active agent:

High temperature resistant slip additive.

### Area of use:

**HECO<sup>®</sup>PRO 020 PP** is suitable for processing polypropylene in injection moulding and extrusion.

### Recommended dose:

**HECO<sup>®</sup>PRO 020 PP** is added in the range of 0.1 - 2.0 % depending on the desired properties. We recommend an addition of 0.75 - 2.0 % for improving the surface scratch resistance.

### Properties:

**HECO<sup>®</sup>PRO 020 PP** is an excellent lubricant and significantly improves the internal melt flow. It reduces surface friction and supports the winding process and the flatness of PP films. Moulded parts get a smooth-res surface appearance and have a significantly higher resistance to scratching

### Pallet size:

1000.0 kg (50 sacks at 20.0 kg) / pallet, net.

### Safety Precautions

#### Foodstuff regulation:

**HECO<sup>®</sup>PRO 020 PP** is compliant with EU Regulation 10/2011. It can be used as an additive in polyolefins in contact with food according to 21 CFR (FDA) Sec. 177.1520 (olefin polymers).

#### Storage:

No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

#### Handling:

The precautions and hygienic measures usual in the handling of any chemical product should be observed.

#### In case of fire:

In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water is unsuitable.

**HECOPLAST<sup>®</sup>** and **HECO<sup>®</sup>** are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features.  
Specific field tests are being recommended under any circumstance.

**HECOPLAST<sup>®</sup>** GmbH Kunststoffadditive, Bremke 17, D - 58638 Iserlohn Telephone + 49 2371 / 797 61-0 – E-Mail: info@hecoplast.de