

# 122 PE

## Slip Additive in PE

**Supplied in shape of:**  
Mixture, Granule.

**Active agent:**  
Slip agent with nucleation aid on a polyethylene carrier.

**Area of use:**  
**HECO**<sup>®</sup>SLIP 122 PE is suitable for processing polyethylene and polypropylene in injection moulding and extrusion.

**Recommended dose:**  
**HECO**<sup>®</sup>SLIP 122 PE is added in the range of 1.0 - 3.0 % depending on the desired properties. We recommend an addition of at least 1.0 - 2.0 %.

**Properties:**  
**HECO**<sup>®</sup>SLIP 122 PE is an external slip agent. It prevents the build-up of colour pigment deposits/residue up into the dead zones. It acts as a form stabiliser and helps to prevent sink marks when demoulded at the right kick-off temperature.

**Pallet size:**  
1000.0 kg (50 sacks at 20.0 kg) / pallet, net.

### Safety Precautions

**Foodstuff regulation:**  
Approval according to EU (VO) No. 10/2011.  
Approval according to the US FDA, see "Food Contact Approvals".

**Storage:**  
No reduction in quality has been reported when properly stored under normal room conditions up to twelve (12) months.

**Handling:**  
The precautions and hygienic measures usual in the handling of any chemical product should be observed.

**In case of fire:**  
In case of fire, suitable extinguishers are aqueous spray, foam or dry chemical; a full jet of water is unsuitable.

**HECOPLAST**<sup>®</sup> and **HECO**<sup>®</sup> are registered trademarks

Our information is based on the most careful analysis, nevertheless these are not guaranteed product features.  
Specific field tests are being recommended under any circumstance.

**HECOPLAST**<sup>®</sup> GmbH Kunststoffadditive, Bremke 17, D - 58638 Iserlohn Telephone + 49 2371 / 797 61-0 – E-Mail: info@hecoplast.de